

*(Effective until July 1, 2020)*

**WAC 51-50-2303 Section 2303—Minimum standards and quality.**

**2303.1.4 Structural glued cross-laminated timber.** Cross-laminated timbers shall be manufactured and identified in accordance with ANSI/APA PRG 320. Cross-laminated timbers in Construction Types IV-A, IV-B, and IV-C shall be manufactured and identified in accordance with ANSI/APA PRG 320 - 18.

[Statutory Authority: RCW 19.27.031 and 19.27.074. WSR 19-02-038, § 51-50-2303, filed 12/26/18, effective 7/1/19.]

*(Effective July 1, 2020)*

**WAC 51-50-2303 Section 2303—Minimum standards and quality.**

**2303.1.4 Structural glued cross-laminated timber.** Cross-laminated timbers shall be manufactured and identified in accordance with ANSI/APA PRG 320. Cross-laminated timbers in Construction Types IV-A, IV-B, and IV-C shall be manufactured and identified in accordance with ANSI/APA PRG 320 - 18.

**2303.6 Nails and staples.** Nails and staples shall conform to requirements of ASTM F1667, including Supplement 1. Nails used for framing and sheathing connections shall have minimum average bending yield strengths as follows: 80 kips per square inch (ksi) (551 MPa) for shank diameters larger than 0.177 inch (4.50 mm) but not larger than 0.254 inch (6.45 mm), 90 ksi (620 MPa) for shank diameters larger than 0.142 inch (3.61 mm) but not larger than 0.177 inch (4.50 mm) and 100 ksi (689 MPa) for shank diameters of not less than 0.099 inch (2.51 mm) but not larger than 0.142 inch (3.61 mm). Staples used for framing and sheathing connections shall have minimum average bending moments as follows: 3.6 in.-lbs (0.41 N-m) for No. 16 gage staples, 4.0 in.-lbs (0.45 N-m) for No. 15 gage staples, and 4.3 in.-lbs (0.49 N-m) for No. 14 gage staples. Staples allowable bending moments shall be listed on the construction documents.

[Statutory Authority: RCW 19.27.031 and 19.27.074. WSR 20-01-090, § 51-50-2303, filed 12/12/19, effective 7/1/20; WSR 19-02-038, § 51-50-2303, filed 12/26/18, effective 7/1/19.]