

**WAC 51-11R-30314 Table R303.1.3(4)—Default U-factors for skylights.**

**TABLE R303.1.3(4)  
DEFAULT U-FACTORS FOR SKYLIGHTS**

Fenestration Type	Frame Type			
	Aluminum Without Thermal Break	Aluminum With Thermal Break	Reinforced Vinyl/ Aluminum-Clad Wood or Vinyl	Wood or Vinyl-Clad Wood/ Vinyl Without Reinforcing
Single Glazing				
glass	U-1.58	U-1.51	U-1.40	U-1.18
acrylic/polycarb	U-1.52	U-1.45	U-1.34	U-1.11
Double Glazing				
air	U-1.05	U-0.89	U-0.84	U-0.67
argon	U-1.02	U-0.86	U-0.80	U-0.64
Double Glazing, e = 0.20				
air	U-0.96	U-0.80	U-0.75	U-0.59
argon	U-0.91	U-0.75	U-0.70	U-0.54
Double Glazing, e = 0.10				
air	U-0.94	U-0.79	U-0.74	U-0.58
argon	U-0.89	U-0.73	U-0.68	U-0.52
Double Glazing, e = 0.05				
air	U-0.93	U-0.78	U-0.73	U-0.56
argon	U-0.87	U-0.71	U-0.66	U-0.50
Triple Glazing				
air	U-0.90	U-0.70	U-0.67	U-0.51
argon	U-0.87	U-0.69	U-0.64	U-0.48
Triple Glazing, e = 0.20				
air	U-0.86	U-0.68	U-0.63	U-0.47
argon	U-0.82	U-0.63	U-0.59	U-0.43
Triple Glazing, e = 0.20 on 2 surfaces				
air	U-0.82	U-0.64	U-0.60	U-0.44
argon	U-0.79	U-0.60	U-0.56	U-0.40
Triple Glazing, e = 0.10 on 2 surfaces				
air	U-0.81	U-0.62	U-0.58	U-0.42
argon	U-0.77	U-0.58	U-0.54	U-0.38
Quadruple Glazing, e = 0.10 on 2 surfaces				
air	U-0.78	U-0.59	U-0.55	U-0.39
argon	U-0.74	U-0.56	U-0.52	U-0.36
krypton	U-0.70	U-0.52	U-0.48	U-0.32

Notes for Table R303.1.3(4)

1. U-factors are applicable to glass and plastic, flat and domed units, all spacers and gaps.
2. Emissivities shall be less than or equal to the value specified.
3. Gap fill shall be assumed to be air unless there is a minimum of 90% argon or krypton.
4. Aluminum frame with thermal break is as defined in footnote 1 to Table R303.1.3(1).

[Statutory Authority: RCW 19.27A.045 and chapter 19.27A RCW. WSR 20-21-081, § 51-11R-30314, filed 10/19/20, effective 2/1/21. Statutory Authority: RCW 19.27A.020, 19.27A.045 and chapters 19.27 and 34.05 RCW. WSR 13-04-055, § 51-11R-30314, filed 2/1/13, effective 7/1/13.]